



Parquet Performance



A single component waterborne lacquer, exhibiting the properties expected from most two pack systems. Giving excellent durability and chemical resistance.

- Latest generation system, combining two pack performance in a single mix
- Fast drying 1½ hours between coats
- Ultra durable, excellent chemical and wear resistance
- Suitable for high traffic areas, including sports floors
- Meets BS7044 (Part 4) 1990 for slip resistance

Available as a gloss, satin and matt finish.

A one pack which performs as a two pack

All the properties of a two pack product within a single pack

Uses

Designed for application to internal hardwood or softwood floors in domestic and a wide range of commercial uses such as shops, offices, restaurants, public buildings and gymnasiums / sports floors (satin and gloss only.)

Not suitable for use on areas where regular contact with water is likely, e.g. bathrooms.

For other uses, please contact our technical department for advice.

Preparation

New Floors

The surface to be finished must be clean, dry and free from contamination. Pre-sand using 100 or 120 grit paper and remove sanding dust prior to application.

Previously Finished Floors

It is very important to remove all traces of wax or polish and to ensure that the previous coating is sound. Wash with white spirit to remove all traces of wax/polish and sand thoroughly using 100 or 120 grit paper. Ensure the surface is clean and dry and remove all sanding dust. It is recommended that a test area is finished to check the adhesion of the lacquer to the previous coating. Ensure good ventilation if using white spirit to remove old polish.

If in doubt, sand the floor back to bare timber, removing all the old coating then treat as a new floor.

Application

Apply by brush or lambs wool mop applicator.

Light traffic: Apply 2 coats

Normal traffic: Apply 3 coats

Heavy traffic: Apply 4 coats

The lacquer should be lightly abraded between coats using 120 or 150 grit paper.

The lacquer may require thinning with up to 5% water, depending upon application method. Do not use in areas of high humidity or condensation.

Drying

Recoatable from 1½ hours onwards under normal drying conditions (20°C and 60% RH).

The finished floor will take normal foot traffic after overnight drying but may remain susceptible to marking by furniture, carpets, rugs etc. until fully cured approximately three days after finishing.

Drying times will be extended under conditions of low temperature or high humidity.

A minimum temperature of 15°C is needed during application and drying.

Other

Coverage

8 - 12 sq. metres per litre depending upon the surface and application.

Cleaning Equipment

Tools, brushes etc. may be cleaned using water containing a small amount of detergent.

Storage

Store away from frost and direct sunlight.

Maintenance

Vacuum clean or wipe with a damp cloth or mop. Do not over-wet the floor. If after a period of time, the floor starts to show signs of wear, a further coat of lacquer can be applied after preparation as detailed above. Floors can be polished if desired.

Health & Safety

Refer to separate health and safety data sheets.

