



BONA PARQUET DÉCOR

Product Description

Features

Bona Parquet Décor is a staining system designed to offer the possibility of changing the look of porous, light wooden floors sanded back to bare wood. Bona Parquet Décor is available in 8 shades including Neutral and is used in a system with either Bona Prime Intense and Traffic or Bona oils (Carl's 90, 45). All the shades can be mixed with each other and can also be diluted with Neutral to reduce the pigment intensity and therefore customize the appearance.

- Less than 10% solvents
- Available in 8 shades including neutral
- Can be used with Bona waterborne finish or Bona oils
- Easy to apply – little risk of overlapping
- Practically no bleed-back
- Excellent coverage rate

Shades



Neutral




White



Acacia



Teak



Mahogany



Paduk



Wenge/Panga-Panga



Ebony

Technical Data

Solids content:	Ca. 90 %
Drying time:	Overcoating with finish - Minimum 48 hours at 20°C/60% R.H. before overcoating Treating with Carl's Oil - Not applicable
Application tools:	Buffing machine, stainless steel trowel or solvent-resistant hard rubber applicator
Application rate:	Ca. 40 m ² /litre
Cleaning of tools:	Tools should be cleaned in White Spirit immediately after application. Use acetone for dried stain
Safety:	Unclassified
Fire risk:	Yes (see the Safety Data Sheet)
Flash point:	56°C
Shelf life:	1 year from date of production in unopened original container
Storage/transport:	The temperature must not fall below +5°C or exceed +25°C during storage and transport
Pack size:	6 x 1 litre (72 boxes per pallet)



BONA PARQUET DÉCOR

Sitework

Surface preparation

- The final colour achieved depends on the original wood - colour, structure etc and the quality/level of sanding.
- Before the work is started the end customer should be shown a prepared sample, both stained and coated, of the actual wood to be treated.
- Keep the coverage rate as recommended (ca. 40 m²/litre). Using more product than recommended will increase the drying time.
- On larger surfaces, the application of stain should be carried out by several people or alternatively the surface should be split into smaller sections.
- If new shades are created by mixing two shades, or using Neutral, or if more than one can is to be used to complete the job **all** the required materials must be mixed into one container before beginning the staining process.
- Bona does not recommend the use of Bona Parquet Décor White on white oak due to excessive colour variation.

Application and directions for use

1. The surface which is to be treated must be even (i.e. not brushed or similar), well sanded, dry and free from sanding dust, oil, wax and other contamination. The final sanding shall be done with a belt sander grit P100 followed by a sanding screen grit P120.
Note: It is recommended to fill all joints with Bona Mix&Fill when using the stain to avoid possible bleed back.
2. Stir the stain well before, and shake occasionally during, use.
3. If the floor is to be treated with oil go to **point 9** from here. If the floor is to be coated with finish continue with **point 4**.
4. Apply **one** coat of stain evenly and thinly over the whole floor using a stainless steel trowel or a buffing machine (100-200 rpm). Put a Bona Oil cloth on the floor, put a pad - with the centre removed - on the cloth and then pour 0,1 litre stain in the middle of the pad. Distribute to ca. 5 m² at a time, add more stain as required. The stain along the edges can be applied using a brush.
Note: When using Bona Parquet Décor White, trowel application should be used for best result.
5. Within 15 minutes from the application, buff the floor using a new clean Bona Abrasive red pad followed by removal of **all** remaining surplus stain using a Bona Oil cloth placed around a clean pad under the machine. **Note: Failure to remove all surplus stain may result in poor adhesion of Bona Prime Intense.**
6. Allow the stain to dry for **at least 48 hours**. Ensure good ventilation and avoid foot traffic throughout the drying time.
7. Buff the floor using a buffing machine (100-200 rpm) and a Bona Abrasive red pad.
8. Apply one coat of Bona Prime Intense followed by a light abrasion with the Bona Scrad System P150 and two coats of Bona Traffic in accordance to respective label instruction.

Using Carl's 45 or Carl's 90

9. Apply the stain using a solvent-resistant hard rubber applicator.
10. Add 20 % Bona Parquet Décor, as used on the floor, to either Carl's 90 or 45 and apply as detailed on the product label, wet-in-wet. To avoid removal of pigment when buffing the floor, use a Bona Abrasive red pad instead of a brown pad.

WARNING: Bona Parquet Décor contains drying oils. Risk of self-ignition. Used cloths, rags and similar should be placed in water or sealed metal containers.

Note: Bona Parquet Décor is designed to be used as a system. Failure to complete each step noted within the instructions correctly could affect both the appearance of the floor and the performance/adhesion of the chosen coating system.