



CARL'S HARD WAX OIL

Sitework

Preparations

The surface which is to be treated must be well sanded, dry and free from sanding dust, old finish and other contamination. The Bona Scrad system, sanding disc/screen or abrasive grade. no 120 should be used for the final sanding of the wood. Product, room and floor temperature should be between 8°C – 35°C. Ensure good ventilation at all times during the application and drying/curing time.

Application

It is suggested that the application is made using a good quality brush with tightly packed fine bristles or a short haired mohair roller. Stir the can well before and during use. Ca. 1 litre/20 – 24 m² per coat, depending upon the wood type

1. Apply a thin even coat across the whole floor avoiding accumulations of product. Apply with the direction of the grain where possible.
2. Leave to dry for a minimum 3-4 hours. Low airflow, low temperature or high humidity may extend the drying/curing time.
3. Distribute another thin coat across the floor in the same manner as the first.
4. Do not traffic the floor until it has had at least 8 hours drying time. It is preferable to leave it longer, where possible.
5. To enhance the sheen it is possible to buff the floor gently when dry using a cloth or a buffing machine with a white pad.

Notes

- As certain dense and/or oily timbers such as wenge, merbau, ipe etc may exhibit variations in absorption and drying, always test timbers like these and the like for function and appearance prior to application of Carl's Hard wax oil. Often only a single application and buffing is necessary to obtain a good surface.
- Where a glossier appearance is desired, Carl's Hard Wax Oil Refresher may be used. First allow the new hard wax oil surface to cure for a week. Apply the Refresher thinly and allow to dry. Polish using a cloth or buffing machine.

WARNING: Carl's Hard Wax Oil contains drying oils. Risk of self-ignition. Used cloths, rags and other contaminated materials should be placed in water or sealed metal containers.

Maintenance

Clean the floor on a daily basis using a dry mop and/or a vacuum cleaner. When necessary wipe off with a damp mop with Carl's Cleaner added to the cleaning water. Note: Always clean using as dry a method as possible. The floor should be maintained on a regular basis using Carl's Hard Wax Oil Refresher. Heavily worn areas (not worn down to the bare wood) may be renovated by abrading the whole surface lightly using a screen grit 150, vacuum clean and re-apply another coat of Carl's Hard Wax Oil, starting from point 3 in the instruction above.

Cleaning

Tools should be cleaned in White Spirit immediately after application.

Contains 2-butanonoxime. May produce an allergic reaction.