



BONA SPORTIVE PRIMER

Sitework

Surface preparation

The surface which is to be coated must be sanded back to bare wood, dry and free from sanding dust, oil, wax and other contamination. The Bona Scrad system, sanding disc/screen or sandpaper grade no. 120 or finer should be used for the final sanding of the wood. The best results are obtained using a buffing machine.

Application

Ensure that the container is shaken thoroughly prior to use (or before decanting smaller quantities). Application should be carried out using a Bona Roller or Bona Applicator Bar. Apply the finish evenly with a smooth flowing action avoiding accumulations of finish. **Note:** The room and finish temperature must not fall below +13°C during application and drying. It is also essential that adequate ventilation be maintained during, and for one week after, application.

Application rate: 8-10 m²/litre (120-100g/m²).

Drying time: 2 - 2½ hours at 20°C/60% RH.

After the application of Sportive Primer a light sanding may be carried out using the Scrad system or a sanding disc/screen grade no. 120 or finer. Alternatively the sanding may take place after the first top coat application.