

General Description

Junckers PRO SEAL is a quick-drying primer designed for professional use in combination with HP COMMERCIAL or HP SPORT.

Compared to similar products Junckers PRO SEAL contains solvents with milder odour and solvency power.

Technical Data

Product:	Air-drying alkyd in low odour solvents.
Package sizes:	5 and 10 litres.
Appearance:	Colourless.
Coverage:	10 m ² per litre.
Application tools:	Brush, mohair roller, air/airless spray.
Substrate temperature:	Minimum 10°C.
Dilution:	Junckers PRO SEAL is delivered ready for use. The mixture can be thinned with max. 5% Junckers THINNER 008.
Drying time:	At 23°C, 50%RH: Sanding: Approx. 6 hours. Re-coating: 6 hours.
Cleaning of tools:	Junckers THINNER 007.
Storage:	Lasts for several years if unopened and stored at 20°C.

System Recommendations

- High traffic areas:** 1 coat PRO SEAL 10 m²/ltr.
2 coats HP COMMERCIAL 10 m²/ltr.
- Low traffic areas:** 1 coat PRO SEAL 10 m²/ltr.
1 coat HP COMMERCIAL 10 m²/ltr.
- Sport:** 1 coat PRO SEAL 10 m²/ltr.
2 coats HP SPORT 10 m²/ltr.

Directions for Use

Untreated/sanded floors

Ensure that the surface is absolutely clean, dry and free from dust, wax, grease, polish etc. Sand away wax, oil stains, lacquer residue etc. Vacuum sanding dust. Apply Junckers PRO SEAL and allow drying. Sand with fine paper (grain 120-180) longitudinally to the fibres of the wood before applying further coats of either HP COMMERCIAL or HP SPORT according to above System Recommendations.

Previously lacquered floors:

Machine sand before lacquering with Junckers PRO SEAL. Use grain size 24 to strip old coats. Then remove abrasion marks with grain size 60. Finally, use grain size 120-180 to obtain a completely smooth surface. Vacuum sanding dust and wipe with a well wrung cloth and clean water. Then seal the floor as described under "Untreated/Sanded floors".

Important!

Before use of the product, read the label on the container carefully and observe the advised precautional safety measures.