



General Description

Junckers PROFESSIONAL 625 is a quick-drying, two-component, acid-curing floor lacquer designed for the professional user.

Junckers PROFESSIONAL 625 provides a hard-wearing lacquer surface.

Compared to similar products Junckers PROFESSIONAL 625 contains solvents with milder odour and solvency power.

Technical Data

Product:	2-component, acid-curing lacquer. Lacquer and hardener are supplied in 2 separate containers to be mixed before use.
Package sizes:	1 + 0.04 litre, 5 + 0.2 litres, 10 + 0.4 litres.
Appearance:	Colourless.
Gloss:	Approx. 20 (Matt) Approx. 40 (Silk-Matt) Approx. 90 (Gloss) Method: DIN 67 530, 60° measuring head.
Mixing:	Shake or stir lacquer part well. Mix 25 parts of PROFESSIONAL 625 Lacquer to 1 part of PROFESSIONAL Hardener 925 and stir continuously.
Pot-life:	24 hours at 20°C.
Coverage:	10 m ² per litre.
Application tools:	Brush, mohair roller, air/airless spray.
Substrate temperature:	Minimum 5°C.
Dilution:	PROFESSIONAL 625 and Hardener 925 are delivered ready for use. The mixture can be thinned with max. 10% Junckers THINNER 006.
Drying time:	Sanding: 1 hour. Recoating: 1½ hours. Light traffic: 24 hours. Maximum hardness achieved after 72 hours.
Cleaning of tools:	Junckers THINNER 007.
Storage:	Lasts for several years if unopened and stored at 20°C.

System Recommendations

Domestic areas: 2 coats Junckers PROFESSIONAL 625 10 m²/ltr.

Sport, commercial and high traffic areas: Not recommended to be used.

Directions for Use

Untreated/sanded floors

Ensure that the surface is absolutely clean, dry and free from dust, wax, grease, polish etc.. Machine sand the surface to remove dirt and irregularities. Vacuum thoroughly.

Shake or stir lacquer part well. Mix lacquer and hardener whilst stirring continuously. Apply a coat of Junckers PROFESSIONAL 625 and allow drying. Sand with fine paper (grit 120-180) longitudinally to the fibres of the wood. Vacuum sanding dust and wipe with a well wrung out cloth and clean water. Apply a further coat of Junckers PROFESSIONAL 625.

Previously lacquered floors

Machine sand by first using grit 24 to strip old coats. Then remove abrasion marks with grit. Finally, use grit 120-180 to obtain a completely smooth surface. Vacuum thoroughly. Treat the floor as described under “Untreated/sanded floors.

Important!

Before use of the product, read the label on the container carefully.

Important!

When using Gloss 90 a light sanding is highly recommended before applying the lacquer, especially when using more than two coats.

Note!

If a more full-bodied finish is wanted, PROFESSIONAL 625, Matt (Gloss 20) can be used as a primer, before applying the final coat.