

## General Description

Junckers Oil Lacquer is a hard-wearing urethane alkyd lacquer for wooden floors, cork-tiled floors and all kinds of interior wood required to be of high wearing quality.

## Technical Data

<b>Product:</b>	Urethane alkyd
<b>Package sizes:</b>	2.5 litres, 5 litres, 10 litres and 25 litres.
<b>Gloss:</b>	Mat, approx. 20 Silk mat, approx. 50
<b>Appearance:</b>	Colourless: the lacquer has a dark colour in the tin but becomes lighter when dry.
<b>Coverage:</b>	Approx. 10m <sup>2</sup> per litre.
<b>Application tool:</b>	Brush or mohair roller.
<b>Surface temperature:</b>	Minimum 10°C.
<b>Dilution:</b>	Delivered ready for use. Dilution is not recommended.
<b>Drying time:</b>	The lacquer is dry for light use after approx. 6 hours at room temperature. Maximum wearing hardness is achieved after 5 days.
<b>Cleaning of tools:</b>	Clean immediately after use with white spirit.
<b>Storage:</b>	Lasts for several years if unopened and stored at 20°C. Please note that once opened the oil will start to harden and cannot then be used after a period of time.

Keep out of the reach of children. If swallowed, seek medical advice immediately and show this package or label.

**System Recommendations**

**All areas:** 2-3 coats Junckers Oil Lacquer -  
10m<sup>2</sup> per litre.

**Directions for Use**

**Surface treatment of primed wood:**

Ensure that the floor is clean, dry and free from dust, grease, wax, polish and soap remnants. Use Junckers NEUTRALIZER for the final washing. Sand with fine sandpaper (grain 120-180) prior to lacquering with Junckers Oil Lacquer. Stir the lacquer well before use.

To ensure optimum adhesion and appearance it is recommended to perform trial applications on a couple of areas, 2 coats at a 6-hour interval. After drying the areas are checked for adhesion by scraping with the edge of a coin. If the adhesion is good and the surface is acceptable, the whole floor can be lacquered 1-2 times.

**Untreated/sanded floors**

Ensure that the surface is absolutely clean, dry and free from all dust, wax, grease, polish and soap remnants, etc. Sand away wax, oil stains, lacquer residue, etc. Vacuum sanding dust.

Apply a coat of Junckers Oil Lacquer and allow drying (approx. 6 hours). Sand with fine sandpaper (grain 120-180) along the fibres of the wood. Vacuum sanding dust or wipe with a well-wrung cloth and clean water. Apply a further 2 coats of Junckers Oil Lacquer.

**Machine sanding:**

Machine sand floors previously treated with wax or polish prior to lacquering. This also applies to floors with flaking lacquer. Then apply lacquer as described under "Untreated/sanded floors".

**Cleaning and maintenance:**

Vacuum daily or wipe with a well-wrung cloth. Clean extremely dirty floors with Junckers CLEANER. Use as little water as possible. When using other cleaning products, it should be ensured that they can be removed prior to new lacquering. Do not clean newly lacquered floors until 5 days after lacquering.

Scuffs and stains from rubber soles or shoe polish or similar are removed with white spirit.

It is not recommended to use products containing wax or polish in connection with maintenance.