



SikaBond®-T52

High viscous (thixotropic) elastic adhesive for wood flooring

Product Description

SikaBond®-T52 is a one part, solvent free, elastic adhesive.

Uses

Full Surface Bonding:

- The laying system for solid- and engineered wood floors (strips, longstrips, planks, panels, boards), mosaic parquet, industrial parquet, wood paving (residential) as well as chipboards.

Sika® AcouBond®-System:

- The laying System for solid wood boards, 3-ply engineered wood as well as chipboards.

For detailed application instructions consult the Product Data Sheet of the Sika® AcouBond®-System, or contact our Technical Service.

Cordon Application:

- The laying System for solid wood boards, 3-ply engineered wood as well as chipboards.
- Elastic Bonding of skirting boards / baseboards and thresholds.

Characteristics / Advantages

- 1-part, ready to use
- Solvent free
- Very low emission EC-1
- Odourless
- Elastic, footfall-sound-dampening adhesive
- Suitable for common types of wood floors
- Especially for problematic wood such as beech and bamboo
- Suitable for bonding wood floors directly onto old ceramic tiles
- Reduces stress on the substrate: the elastic, material-compatible adhesive reduces transverse stress between the wood floor and the substrate
- Suitable for subfloor heating
- Compensation of small substrate unevenness
- Adhesive can be sanded

Tests

Approval / Standards

EMICODE EC 1 "very low emission".
GISCODE PU 10 "solvent free".

Construction



Product Data

Form

Colour	Parquet brown
Packaging	13 kg metal pails (=10.1 litre) 600 ml sausages (20 sausages per box)

Storage

Storage Conditions / Shelf Life	9 months from date of production if stored in undamaged original sealed containers, in dry conditions and protected from direct sunlight at temperatures between +10°C and +25°C.
--	---

Technical Data

Chemical Base	1-part Polyurethane, moisture curing.
Density	~ 1.29 kg/l (DIN 53 479)
Skinning- / Laying Time	~ 60 - 90 minutes (+23°C / 50% r.h.)
Curing Rate	~ 3.0 mm / 24h (+23°C / 50% r.h.) Floor may be walked on / sanded 24-48 hours after installation (depending on climatic conditions and adhesive layer thickness).
Sag Flow	Consistency: Spreads easily, trowel marks stable. easily applicable with gun.
Service Temperature	-40°C to +70°C

Mechanical / Physical Properties

Shear Strength	~ 0.7 N/mm ² , 1 mm adhesive thickness (+23°C / 50% r.h.) (DIN 281)
Tensile Strength	~ 1.3 N/mm ² (+23°C / 50% r.h.) (DIN 53 504)
Shore A Hardness	~ 30 (after 28 days) (DIN 53 505)
Elongation at Break	~ 900% (+23°C / 50% r.h.) (DIN 53 504)

System Information

Application Details

Consumption	<p>Sika® AcouBond-System: 500 - 600 g/m² (400 - 500 ml/m²). Filling of all cut-outs is a must. Use triangular nozzle with 8 x 10 mm opening.</p> <p>Full Surface Bonding: 700 - 900 g/m² with notched trowel B3 (acc. to IVK guidelines) or 3/16" 1/8" 1/8" (engineered strips / planks, mosaic parquet) 800 - 1000 g/m² with notched trowel B11 (acc. to IVK guidelines), AP 48 or 3/16" 3/16" 3/16" (solid wood, engineered longstrips / panels, industrial parquet, wood paving (residential), chipboards)</p> <p>For bonding of long, width boards or in case of uneven substrates it could be necessary to use a notched trowel with bigger notches (avert hollow sections).</p> <p>Cordon Application: Approx. 44 ml per running meter = 250 - 500 g/m², dependent on cordon interval (solid wood boards, 3-ply engineered wood, chipboards)</p> <p>For substrates prepared with Sika® Primer MB, the consumption of SikaBond®-T52 is lower.</p>
--------------------	---

Substrate Quality	Clean and dry, homogeneous, even, free from grease, dust and loose particles. Paint, laitance and other poorly adhering particles must be removed. Standard construction rules must be observed.
--------------------------	---

Substrate Preparation	<p>Concrete / cement screed: Must be ground and thoroughly cleaned with industrial vacuum cleaner.</p> <p>Anhydrite screed / Anhydrite flowable screed: Must be ground and thoroughly cleaned with industrial vacuum cleaner shortly before bonding starts.</p> <p>Broadcast mastic asphalt: Must be primed with Sika® Primer MB. Instructions for use, see Product Data Sheet for Sika® Primer MB.</p> <p>Glazed ceramic and old ceramic tiles: Degrease, clean with SikaCleaner® or grind the tile-surface and clean thoroughly with an industrial vacuum cleaner.</p> <p>Wood- / gypsum boards (e.g. chipboards, plywood): Glue / screw the boards to the substructure. They have to be fixed on the substrate. In case of floating subfloors, please contact our Technical Service.</p> <p>Unknown substrates: Please contact our Technical Service.</p> <p>SikaBond®-T52 can be used without priming on cement floors, anhydrite floors, chip boards, concrete and ceramic tiles.</p> <p>For broadcast mastic asphalt, cement floors with an excessive moisture content, as well in case of renovation on old adhesive residues and on structurally weak substrates use Sika® Primer MB. For detailed instructions consult the Product Data Sheet of Sika® Primer MB or contact our Technical Service.</p>
Application Conditions / Limitations	
Substrate Temperature	<p>During laying and until SikaBond®-T52 has fully cured substrate temperature must be > + 15°C and in case of floor heating < + 20°C.</p> <p>For Substrate temperatures the standard construction rules are relevant</p>
Ambient Temperature	<p>Room temperature between +15°C and +35°C.</p> <p>For ambient temperatures the standard construction rules are relevant.</p>
Substrate Humidity	<p>Permissible substrate moisture content :</p> <ul style="list-style-type: none"> - 2.5% CM for cement screed (ca. 4% Tramex / Gravimetric weight percent) - 0.5% CM for anhydrite screed - 3 - 12% CM for magnesia flooring (proportion of organic parts) <p>Permissible substrate moisture content in case of floor heating:</p> <ul style="list-style-type: none"> - 1.8% CM for cement screed (ca. 3% Tramex / Gravimetric weight percent) - 0.3% CM for anhydrite screed - 3 - 12% CM for magnesia flooring (proportion of organic parts) <p>For moisture content and quality of substrates the guidelines of wood floor manufacturer as well as standard construction rules must be observed.</p>
Relative Air Humidity	<p>Between 40% and 70%</p>

Application Instructions

Application Method / Tools

Sika® AcouBond®-System
For detailed application instructions consult the Product Data Sheet of the Sika® AcouBond®-System, or contact our Technical Service.

Full Surface Bonding

SikaBond®-T52 is applied to the properly prepared substrate directly from the pail and uniformly distributed by notched trowel. Press the wood floor elements firmly into the adhesive so that the underside is fully wetted. The elements can then be joined together using a hammer and a impact block. Many types of wood floors have to be tapped from the top. A distance of 10-15 mm from the wall to the wood floor must be observed.

Cordon Application:

After the preparation of sausage and gun, extrude a triangular shaped cordon of adhesive approximately 10 mm high and 8 mm wide at 100-250 mm centres (dependent on wood floor type) on the properly prepared subfloor. Press the wood floor elements firmly in to the adhesive (at right angles with adhesive cordons). The elements can then be joined together using a hammer and a impact block. The required distance from the wall to the wood floor in the laying instruction from the wood floor manufacturer must be observed.

Fresh, uncured adhesive remaining on the wood floor surface must be removed immediately with a clean cloth and if necessary cleaned with Sika® Remover-208 or Sika® Handclean cloths. Test wood floor surfaces for compatibility with Sika® Cleaner-208 before use.

The laying instructions of the wood floor manufacturer as well as standard construction rules must be observed.

Cleaning of Tools

Clean all tools and application equipment with Sika® Remover-208 immediately after use. Hardened / cured material can only be mechanically removed.

Potlife

~ 60 minutes

Notes on Application / Limitations

SikaBond®-T52 is only suitable for experienced applicator.

If, according to wood floor suppliers or producers deviation from the standards is permissible, temperatures between +5°C and +35°C must be observed for the adhesive.

For better workability the adhesive temperature must be at least +15°C.

For the proper curing of the adhesive sufficient ambient moisture is necessary.

For AcouBond-System and Cordon Application accurate tongue and groove (min. 3 x 3 mm) are inevitable:

Minimum wood size: length over 3 adhesive cordons
 width > 50 mm
 thickness > 12 mm

Maximum wood size: thickness < 28 mm

Wood floors in non insulated areas such as basements, or other areas without a damp proof membrane, must only be installed after the application of Sikafloor® EpoCem sealed with Sika® Primer MB to control the moisture. For detailed instructions consult the Product Data Sheets or contact our Technical Service.

In case of chemically pre-treated types of wood floors (e.g. ammonia, wood stain, timber preservative) and woods with high oil content SikaBond®-T52 is only to be used after a written recommendation from our Technical Service.

Do not use on PE, PP, TEFLON, and certain plastized synthetic materials (carry out pre-trials or contact our Technical Service).

Some primers can negatively influence the adhesion of SikaBond®-T52 (pre trials recommended).

Notes

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information

Protective Measures	To avoid rare allergic reactions, we recommend the use of protective gloves. Change soiled work clothes and wash hands before breaks and after finishing work. Local regulations as well as health and safety advice on packaging labels must be observed.
Ecology	Refer to Material Safety Data Sheet.
Transportation Class	Refer to Material Safety Data Sheet.
Important Notes	Residues of material must be removed according to local regulations. Fully cured material can be disposed of as household waste under agreement with the responsible local authorities. Detailed health and safety information as well as detailed precautionary measures e.g. physical, toxicological and ecological data can be obtained from the material safety data sheet.
Toxicity	Refer to Material Safety Data Sheet.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Limited
 Watchmead
 Welwyn Garden City
 Hertfordshire
 AL7 1BQ
 United Kingdom

Phone +44 1707 394444
 Telefax +44 1707 329129
www.sika.co.uk, email: sales@uk.sika.com

